

**SEAL-BLOCK INSULATION**

**Underwriters Laboratories Testing Information**



**R-8078 Underwriters Laboratories Inc. R-26300**  
Classified Batt and Blanket Material

ASTM E 84, UL 723

**FLAME SPREAD 10**  
**SMOKE DEVELOPED 50**

See the UL Directory BKNV Listings  
Manufactured by Cellulose Material Solutions

---

**Additional Testing: SEAL BLOCK INSULATION**

**Flammability Characteristics**

- Critical Radiant Flux: Greater than or equal to 0.12 w/cm<sup>2</sup>      ASTM E 970
- Smoldering Combustion: Less than or equal to 15.0%      ASTM E 739

**Environmental Characteristics**

- Corrosiveness: Acceptable      ASTM C 739
- Fungal Growth: Acceptable      ASTM C 1338

**Physical Characteristics**

- Design Density 3.5 pounds/ft<sup>3</sup>      ASTM C 167
- Thermal Resistance: 3.7 R (in.) R-11 @ 3.0 (in.)      ASTM C 518
- Moisture Absorption: Acceptable      ASTM C 739
- Odor Emission: Non-Apparent      ASTM C 1304

**SEAL-BLOCK INSULATION**

**Underwriters Laboratories Testing Information**



**R-8078 Underwriters Laboratories Inc. R-26300**  
Classified Batt and Blanket Material

ASTM E 84, UL 723

**FLAME SPREAD 10**  
**SMOKE DEVELOPED 50**

See the UL Directory BKNV Listings  
Manufactured by Cellulose Material Solutions

---

**Additional Testing: SEAL BLOCK INSULATION**

**Flammability Characteristics**

- Critical Radiant Flux: Greater than or equal to 0.12 w/cm<sup>2</sup>      ASTM E 970
- Smoldering Combustion: Less than or equal to 15.0%      ASTM E 739

**Environmental Characteristics**

- Corrosiveness: Acceptable      ASTM C 739
- Fungal Growth: Acceptable      ASTM C 1338

**Physical Characteristics**

- Design Density 3.5 pounds/ft<sup>3</sup>      ASTM C 167
- Thermal Resistance: 3.7 R (in.) R-11 @ 3.0 (in.)      ASTM C 518
- Moisture Absorption: Acceptable      ASTM C 739
- Odor Emission: Non-Apparent      ASTM C 1304